



鑫寶發興業有限公司

SAMPLE FINE ENTERPRISE CO., LTD.

台北市金山南路二段 138 號 5F 之 1

TAIPEI OFFICE: 5F-1. NO.138. SEC.2. CHIN SHAN S. RD.,
TAIPEI TAIWAN, R.O.C

TEL: (02)23920707(代表號)
FAX: (02)23223373
E-MAIL: spf0707@ms48.hinet.net

FINESORB 2250-4

Appearance *Pale yellow crystalline powder*

Assay (GC) *99% min.*

Melting Point *128-132 °C*

Ash *0.1% max.*

Loss on Drying *0.5% max.*

Transmittance (5g/100ml Toluene; 1cm cell)

440 nm *95% min.*

500 nm *97% min.*

Package *25 Kgs net/fiber drum.*

Uses

It is a highly efficient UV-absorber for styrenic polymers, PVC, unsaturated polyesters, PU, acrylic polymers, polycarbonates, adhesives and coatings.



鑫寶發興業有限公司


SAMPLE FINE ENTERPRISE CO., LTD.

台北市金山南路二段 138 號 5F 之 1

TAIPEI OFFICE: 5F-1. NO.138. SEC.2. CHIN SHAN S. RD.,
TAIPEI TAIWAN, R.O.C

TEL: (02)23920707(代表號)
FAX: (02)23223373
E-MAIL: spf0707@ms48.hinet.net

UV Absorption Spectrum



(0.005 g/1000 ml Methanol)

λ 238 nm

$\epsilon = 14,045$

λ 241 nm

$\epsilon = 13,961$

λ 297 nm

$\epsilon = 19,614$

λ 337 nm

$\epsilon = 20,886$

Storage

Shelf life for at least 1 year when it's stored in closed containers in room temperature and dry conditions.

Health and Safety Information

Please refer to our Material Safety Data Sheet.